


锁定和密封

ND Microspheres TA系列产品是压克力基，于室温固化胶粘剂，可以应用于所有大小、组合、材料和表面处理。预涂NDTA胶的紧固件是表面干燥和随时可组装。



ND Microspheres TA系列产品功能双微型胶囊-树脂胶囊和活化剂胶囊结合在一起的解决方案。组装的力量粉碎了微胶囊，两胶囊之内含物混合产生化学反应而将零件锁住。本系列产品提供一致的和可预测的转矩值，不需要加热或催化剂。

在典型情况下，ND Microspheres TA系列产品在5分钟内开始固化，在24小时内完全固化。

特点:

低旋入扭矩: 和尼龙胶相比，ND微胶囊产品可用常见的手动工具轻易组装。

几个配方: ND微球TA系列提供三个配方来满足不同需求包括: 低强度, 高强度, 耐高温扭矩张力控制。

多功能: ND微胶囊TA系列产品是兼容大部分紧固件尺寸、组合、材料和表面处理。

长保质期: ND微胶囊TA系列涂布于工件尚可维持四年，仍将保持惰性，直到锁入对锁件开始固化。

不受外来物质影响: 交错的分子结构的微胶囊TA系列产品让他成为最耐药类型的粘合剂。完全固化后几乎不受石油、汽油、盐雾、酸、溶剂、水的影响。

省钱: ND微胶囊产品比组装在线使用瓶装快干产品便宜。不需要昂贵的锁紧垫圈，开口销或锁紧螺帽。



规格满足:

AUTOMOTIVE:

- Ford: ESS-M11P24-A2
- General Motors: GM6124M, GM6175M, GM6194M, GME00151, GMW14657A, GMW14657C

INDUSTRIAL FASTENER INSTITUTE:

- IFI 125, IFI 525

OEM:

- Harley Davidson: EG805-34900

规格:

Formula	TA300	TA800	TA850
Color*	Yellow	Red	Turquoise
Competes With	Nylok® Precote® 30, ThreeBond 2471 & 2415	Nylok® Pre- cote® 80	Nylok® Precote® 85, ThreeBond 2403 & 2411
Primary Usage	Low Strength	High Strength	High Strength Tension Control
Prevailing on-torque	<1.13 Nm	<1.13 Nm	<1.13 Nm
Breakaway Torque ** Dry Phosphate	15 Nm	23 Nm	20 Nm
Minimum Temp.	-58° F (-50° C)	-58° F (-50° C)	-58° F (-50° C)
Maximum Temp.	300° F (150° C)	392° F (200° C)	392° F (200° C)
Fixture Time	5 Min.	5 Min.	5 Min.
On-Part Life	4 Years	4 Years	4 Years
Full Cure Time @ R.T.	24 hrs.	24 hrs.	24 hrs.

* Other colors available on request

** After 24 hr. cure at room temp. Based on 3/8 - 16 bolts using plain steel nuts.

ND Microspheres and ND Industries are registered trademarks of ND Industries, Inc.
Nylok is a registered trademark of Nylok, LLC
Precote is a registered trademark of Precote U.S.A.



稳得电子(昆山)有限公司
ND Electronics (Kunshan) Co., Ltd.

中国江苏省昆山市城北玉城中路395号 邮编: 215300 电话: 86-512-5776-5335 传真: 86-512-5775-5353

Web Site: www.ndindustries.com • E-mail: ndchina@ndindustries.com